

9th International Conference on Computational Methods in Structural Dynamics and Earthquake Engineering

A NEW MULTISCALE STEEL-CONCRETE BOND MODEL FOR STRUCTURAL DYNAMICS

Maryam Trad¹, Ibrahim Bitar¹, Stéphane Grange², and Benjamin Richard¹

¹ Institut de Radioprotection et de Sûreté Nucléaire (IRSN), PSN-EXP/SES/LMAPS, B.P. 17 - 92262 Fontenay-aux-Roses Cedex, France

² Univ Lyon, INSA Lyon, GEOMAS, EA7495, 69621 Villeurbanne, France

maryam.trad@irsn.fr

Content




Interest of the subject for dynamic applications: Energy dissipation at the steel-concrete interface level.



Physical description of the interface behavior.



Experimental characterization of the steel-concrete bond.




Numerical strategies proposed in the literature for the interface modeling.



Proposal of a new multiscale modeling strategy of the interface behavior: **principles**.




Proposal of a new multiscale modeling strategy of the interface behavior: **validation examples**.



Proposal of a new multiscale modeling strategy of the interface behavior: **application examples**.

Energy dissipation at the steel-concrete interface level



Interface behavior

Physical description

Frantzeskakis (1987)

Torre-Casanova (2012)

$$\tau = k_1 g - k_2 g^2 + k_3 g^3$$

Nilson (1968)

Experimental tests

- Ties** Clément (1987)
- Pull-out** Dahou et al.(2009)
- PIAF test** Tran et al. (2009)
- Beam tests** Dancygier and Katz (2012)
- Push-in test** Tixier(2015)

Numerical modeling

- Springs** Ngo et Scordelis (1967)
- Joint elements** Dominguez (2005)
- Internal forces** Torre-Casanova (2012)
- 1D steel – 3D point** Mang (2015)
- Homogenization** Sellier et Millard (2019)

Proposal of a new multiscale modeling strategy of the interface behavior: principles

Motivations



- The numerical modeling of the steel-concrete interface behavior is important for a good representation of the concrete cracking and a better estimate of material energy dissipation.
- A representative description of the interface behavior at the scale of an industrial building using existing models is still tedious and impractical.

Principles


One macro-element = an assembly of several biphasic elements

One biphasic element = an assembly of :

- one three-nodes bar elements representing steel;
- one three-nodes bar elements representing the interface;
- bond stresses




Proposal of a new multiscale modeling strategy of the interface behavior: principles




Proposal of a new multiscale modeling strategy of the interface behavior: principles

Principles



Proposal of a new multiscale modeling strategy of the interface behavior: principles

Principles




- For the calculation of F_{int} and k , a local algorithm is called in order to establish the equilibrium of the macro-element (internal force at internal nodes = 0).
- A static condensation technique is used in order to condense the stiffness matrix of the macro-element at its four external nodes.


Proposal of a new multiscale modeling strategy of the interface behavior: validation

Pullout test of Torre-Casanova 2012


Test description



Material parameters




Mesh



Proposal of a new multiscale modeling strategy of the interface behavior: validation

Pullout test of Torre-Casanova 2012


Test description



Material parameters

| Concrete parameters | Description | Value | Unit |
|---------------------|---------------------------|-----------------------------------|------------------|
| E_c | Young's modulus | 28 | GPa |
| ν_c | Poisson's ratio | 0.22 | - |
| f_t | Tensile strength | 3.16 | MPa |
| ϵ_{ad0} | Damage threshold | 1.1143×10^{-4} | - |
| A_t | Local Mazars' model input | Not used - the law is regularized | - |
| B_t | Mazars' model input | Regularized | - |
| A_c | Mazars' model input | 1.1 | - |
| B_c | Mazars' model input | 700 | - |
| β | Mazars' model input | 1.06 | - |
| G_f | Fracture energy | 150 | J/m ³ |
| Steel parameter | Description | Value | Unit |
| E_a | Young's modulus | 200 | GPa |


Mesh




Proposal of a new multiscale modeling strategy of the interface behavior: validation

Pullout test of Torre-Casanova 2012


■ Imposed displacement



■ Reaction



■ Damage




The resultant reaction curve verifies the pullout constitutive equation : $\tau_s = \frac{F}{\varphi \pi l}$


Proposal of a new multiscale modeling strategy of the interface behavior: validation

Pullout test of Torre-Casanova 2012

■ Imposed displacement




■ Reaction




Proposal of a new multiscale modeling strategy of the interface behavior: application

Tie test of Farra 1995


Test description



Material parameters




Mesh



Proposal of a new multiscale modeling strategy of the interface behavior: application

Tie test of Farra 1995


Test description



Material parameters

| Concrete parameters | Description | Value | Unit |
|---------------------|---------------------------|-----------------------------------|------------------|
| E_c | Young's modulus | 30.4 | GPa |
| ν_c | Poisson's ratio | 0.22 | - |
| f_t | Tensile strength | 2.6 | MPa |
| ε_{d0} | Damage threshold | 8.5526×10^{-5} | - |
| A_t | Local Mazars' model input | Not used - the law is regularized | - |
| B_t | Mazars' model input | Regularized | - |
| A_c | Mazars' model input | 1.2 | - |
| B_c | Mazars' model input | 700 | - |
| β | Mazars' model input | 1.06 | - |
| G_f | Fracture energy | 150 | J/m ³ |
| Steel parameter | Description | Value | Unit |
| E_a | Young's modulus | 200 | GPa |



Mesh




Proposal of a new multiscale modeling strategy of the interface behavior: application

Tie test of Farra 1995 – linear concrete behavior

Reactions



Iterations





| Model | Perfect bond | Torre-Casanova 2012 | Mang 2015 | Macro-element |
|------------|--------------|---------------------|-----------|---------------|
| Iterations | 200 | 289 | 299 | 209 |


Proposal of a new multiscale modeling strategy of the interface behavior: application

Tie test of Farra 1995 – linear concrete behavior

Reactions




Iterations




Proposal of a new multiscale modeling strategy of the interface behavior: application

Tie test of Farra 1995 – nonlinear concrete behavior

Concrete damage




Experimental – numerical curves




Proposal of a new multiscale modeling strategy of the interface behavior: application

Beam end test of J. Rex et al. 2019


Test description



Material parameters




Mesh



Proposal of a new multiscale modeling strategy of the interface behavior: application

Beam end test of J. Rex et al. 2019


Test description



Material parameters

| Concrete parameters | Description | Value | Unit |
|---------------------|---------------------------|-----------------------------------|------------------|
| E_c | Young's modulus | 28 | GPa |
| ν_c | Poisson's ratio | 0.2 | - |
| f_t | Tensile strength | 2.565 | MPa |
| ε_{d0} | Damage threshold | 9.1607×10^{-5} | - |
| A_t | Local Mazars' model input | Not used - the law is regularized | - |
| B_t | Mazars' model input | Regularized | - |
| A_c | Mazars' model input | 1.3 | - |
| B_c | Mazars' model input | 650 | - |
| β | Mazars' model input | 1.06 | - |
| G_f | Fracture energy | 150 | J/m ³ |
| Steel parameter | Description | Value | Unit |
| E_a | Young's modulus | 200 | GPa |


Mesh




Proposal of a new multiscale modeling strategy of the interface behavior: application

Beam end test of J. Rex et al. 2019

Concrete damage



Experimental – numerical curves



Conclusions

- The main advantage of the proposed approach to model the steel-concrete interface is that it consists of modeling the steel and the steel-concrete interface within a single finite element, which makes it more practical to introduce the consideration of the interface behavior into a finite element calculation.
- Bond stresses are introduced locally within the macro-element. The studied examples show the robustness of the model and its ability to reproduce the experimental behavior of the interface.

Perspectives

- Application for large-scaled structures subjected to both static and dynamic loads.

Thank you !

References

- M . Huguet Aguilera. Un modèle global homogénéisé pour la fissuration des voiles en béton armé sous chargements sismiques, Ecole Centrale de Nantes, thèse- 2016.
- C. Frantzeskakis. Contribution à la modélisation des structures en béton armé par la méthode des éléments finis, Ecole nationale des ponts et chaussées, thèse- 1987.
- A. Torre-Casanova. Prise en compte de la liaison acier-béton pour le calcul de structures industrielles, Ecole normale supérieure de Cachan - ENS Cachan, thèse-2012.
- A.H. Nilson. Nonlinear Analysis of Reinforced Concrete by the Finite Element Method, ACI Journal, vol 65, p. 757-766, Septembre 1968.
- J.-L. Clément. Interface acier-béton et comportement des structures en béton armé : caractérisation, modélisation, Université Paris 6, 1987.
- Z. Dahou, Z.M. Sbarta, A. Castel, F. Ghomari. Articial neural network model for steel-concrete bond prediction, Engineering structures vol 31, p. 1724-1733, 2009.
- B.H. Tran, Y. Berthaud, F. Ragueneau. Essai PIAF: pour identifier l'adhérence et le frottement, AUGC XXVIIeme Rencontres Universitaires de Genie Civil, 2009.
- A. N. Dancygier, A. Katz, M. Y. Yardimci, D. Z. Yankelevsky. Behavior of high ductility cement composite beams under low impact. *International Journal of Protective Structures*, 3(2), 177-191, 2012.
- A. Tixier. Analyse du comportement de l'interface acier-béton par essai push-in. Mesures par fibres optiques et modélisation par éléments finis, Université de Grenoble, thèse-2013.
- D. Ngo, A. C. Scordelis. Finite Element Analysis of Reinforced concrete beams ACI Journal, Mars 1967.
- H. W. Reinhardt, J. Blaauwendraad, E. Vos. Prediction of bond between steel and concrete by numerical analysis Matériaux et Constructions, 2004.
- N. Dominguez Ramirez. Etude de la liaison acier-béton: De la modélisation du Phénomène à la Formulation d'un Elément Fini Enrichi "Beton-Armé", Laboratoire de mécanique et technologie, Ecole normale supérieure de Cachan - ENS Cachan, thèse-2005.
- C. Mang. Modélisation de la liaison acier-béton dans le calcul de structures en béton armé, Université Paris Ouest, thèse- 2015.
- A. Sellier, A. Millard. A homogenized formulation to account for sliding of non-meshed reinforcements during the cracking of brittle matrix composites: Application to reinforced concrete, Engineering Fracture Mechanics vol 213, p. 182-196, 2019.
- B. Farra. Influence de la résistance du béton et de son adhérence avec l'armature sur la fissuration, Ecole polytechnique fédérale de Lausanne, thèse- 1995.
- J. Rex, A. Sharma, J. Hofmann. A new test specimen to investigate the bond behavior of post-installed reinforcing bars. Structural Concrete, 20(2), 583-596, (2019).